

Description

TPSeal® M4741 UV Black is a new generation High Density Metallocene based Polyethylene with hexene as comonomer. TPSeal® M4741 UV Black is intended for the manufacture of rotomolded items and is available in black powder.

Its specific molecular structure ensures:

- ✓ Superior mechanical properties
- ✓ Improved dimensional stability
- ✓ Easy processing
- ✓ Outstanding ESCR
- ✓ UV protected

Suitable to produce tanks, underground tanks, technical parts, diesel fuel tanks.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 190°C/2.16 kg	ISO 1133-1	g/10 min	4,0
Mechanical properties			
Tensile Modulus – True Stress / True Strain Rotomolded sample	Internal method	MPa	1025
Thermal properties			
Melting Temperature	internal method	°C	128
Heat Deflection Temperature 0,45 MPa - 120°C per hour	ISO 75-2	°C	70
Vicat Softening point A50 (10N, 50°C/h)	ISO 306	°C	120
Bell ESCR (10% Igepal)	ASTM D 1693	F50 in hours	> 1000
FNCT (10% Caflon NP9)	ISO 16770 at 50°C 3,0 MPa	hours	700
Other physical properties			
Density (of the natural material)	ISO 1183	g/cm ³	0,947

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information.

It is advisable to convert the product within one year after delivery, provided storage conditions are used as given in the SDS of our product. SDS may be obtained from your technical service contact on request.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.